



JR Engineering & Medical Technologies (M) Sdn Bhd

Lot 8&10, Jalan Zurah 3& Lot 1&3, Jalan Zurah 3A/1, Pusat
Perindustrian 2, 44200 Rasa Selangor, Hulu Selangor, Selangor Darul
Ehsan, Malaysia Tel: 603-7781 2829 Fax: 603-7781 2830; Website:
www.jr-medical.com

PRODUCT SPECIFICATIONS

Document number :JR-S0004

| | |
|----------------------|---|
| NAME | : 400mm Nitrile Powder Free Gloves -12.0 grams |
| DESIGN | : Ambidextrous. Beaded Cuff |
| SURFACE | : Palm Textured/Finger Textured /Smooth |
| COLOUR | : Natural/Blue |
| PROTEIN LEVEL | : N/A |
| POWDER CONTENT | : Max 2.0 mg/glove |
| FORCE AT BREAK | : Before Ageing :9.0-11.0N After Ageing: 6.0-10.0N |
| TENSILE STRENGTH | : Before Ageing: 18-22 Mpa After Ageing: 14-18 Mpa |
| ELONGATION | : Before Ageing: 650-750 % After Ageing: 500-700 % |
| PERFORMANCE STANDARD | : ASTM D-3578, EN 455-Part 1,2&3 |
| MATERIAL | :100% pure Nitrile |
| DONNING AID | : Chlorinated/Polymer |
| STORAGE CONDITION | : Product shall be stored under room condition, avoid direct sunlight |
| SHELF LIFE | : Product shall have shelf life of 3 years from date of manufacture with the above storage condition. |
| SIZE | :S-Small, M-Medium, L-Large,XL-X Large,XXL-XX Large |
| DIMENSION | : Length: Min 400mm |
| CRITERIA | : Average Width (mm): S-85±3, M-95±3, L-105±3,XL-110±3, XXL-120±3 |
| WEIGHT | : Average Weight (grams): S-11.5±0.5,M-12.0±0.5, L-12.5± 0.5, XL-13.0 ± 0.5,XXL-13.5± 0.5 |
| THICKNESS | : Single Wall thickness (x 0.01mm) Finger thickness:18±3mm Palm thickness:16±2mm |

