



## JR Engineering & Medical Technologies (M) Sdn Bhd

Lot 8&10, Jalan Zurah 3& Lot 1&3, Jalan Zurah 3A/1, Pusat  
Perindustrian 2, 44200 Rasa Selangor, Hulu Selangor, Selangor Darul  
Ehsan, Malaysia Tel: 603-7781 2829 Fax: 603-7781 2830; Website:  
[www.jr-medical.com](http://www.jr-medical.com)

### PRODUCT SPECIFICATIONS

Document number :JR-S0001

NAME	: 300mm Nitrile Powder Free Gloves -5.5 grams
DESIGN	: Ambidextrous. Beaded Cuff
SURFACE	: Palm Textured/Finger Textured /Smooth
COLOUR	: Natural/Blue
PROTEIN LEVEL	: N/A
POWDER CONTENT	: Max 2.0 mg/glove
FORCE AT BREAK	: Before Ageing :9.0-11.0N After Ageing: 6.0-10.0N
TENSILE STRENGTH	: Before Ageing: 18-22 Mpa After Ageing: 14-18 Mpa
ELONGATION	: Before Ageing: 650-750 % After Ageing: 500-700 %
PERFORMANCE STANDARD	: ASTM D-3578, EN 455-Part 1,2&3
MATERIAL	:100% pure Nitrile
DONNING AID	: Chlorinated/Polymer
STORAGE CONDITION	: Product shall be stored under room condition, avoid direct sunlight
SHELF LIFE	: Product shall have shelf life of 3 years from date of manufacture with the above storage condition.
SIZE	:S-Small, M-Medium, L-Large,XL-X Large,XXL-XX Large
DIMENSION	: Length: Min 300mm
CRITERIA	: Average Width (mm): XS-78±3,S-85±3, M-95±3, L-105±3,XL-115±3, XXL-120±3
WEIGHT	: Average Weight (grams): XS±4.5±0.5, S-5.0±0.5,M-5.5±0.5, L-6.0± 0.5, XL-6.5 ± 0.5,XXL-7.0± 0.5
THICKNESS	: Single Wall thickness (x 0.01mm) Finger thickness:12±3mm Palm thickness:9±3mm



JR MEDICAL  
乔润医疗

