



JR Engineering & Medical Technologies (M) Sdn Bhd

Lot 8&10, Jalan Zurah 3& Lot 1&3, Jalan Zurah 3A/1, Pusat

Perindustrian 2, 44200 Rasa Selangor, Hulu Selangor, Selangor Darul

Ehsan, Malaysia Tel: 603-7781 2829 Fax: 603-7781 2830; Website:

www.jr-medical.com

PRODUCT SPECIFICATIONS

Document number :JR-S0002

NAME	: Latex 240mm EXam Gloves Powder Free -5.5 grams
DESIGN	: Ambidextrous. Beaded Cuff
SURFACE	: Palm Textured/Finger Textured /Smooth
COLOUR	: Natural/Blue/Black/Green
PROTEIN LEVEL	: Max 50 Microgram/d m ²
POWDER CONTENT	: Max 2.0 mg/glove
FORCE AT BREAK	: Before Ageing :6.0-9.0N After Ageing: 6.0-9.0N
TENSILE STRENGTH	: Before Ageing: 18-22 Mpa After Ageing: 14-18 Mpa
ELONGATION	: Before Ageing: 650-800 % After Ageing: 500-750 %
PERFORMANCE STANDARD	: ASTM D-3578, EN 455-Part 1,2&3
MATERIAL	: Natural Rubber Latex
DONNING AID	: Chlorinated/Polymer
STORAGE CONDITION	: Product shall be stored under room condition, avoid direct sunlight
SHELF LIFE	: Product shall have shelf life of 3 years from date of manufacture with the above storage condition.
SIZE	:XS-X small, S-Small, M-Medium, L-Large XL-X Large
DIMENSION	: Length: Min 240mm
CRITERIA	: Average Width (mm): XS-77±3, S-83±3, M-95±3, L-106±3, XL-112±3
WEIGHT	: Average Weight (grams): XS-4.5± 0.5, S-5.0±0.5, M-5.5±0.5, L-6.0± 0.5, XL-6.5 ± 0.5
THICKNESS	: Single Wall thickness (x 0.01mm) Finger thickness:12±3mm Palm thickness:10±3mm



JR^{E D I C A L} 杰润医疗

