



JR Engineering & Medical Technologies (M) Sdn Bhd

Lot 8&10, Jalan Zurah 3& Lot 1&3, Jalan Zurah 3A/1, Pusat

Perindustrian 2, 44200 Rasa Selangor, Hulu Selangor, Selangor Darul

Ehsan, Malaysia Tel: 603-7781 2829 Fax: 603-7781 2830; Website:

www.jr-medical.com

PRODUCT SPECIFICATIONS

Document number :JR-S0006

NAME	: 240mm Nitrile Exsm Gloves Powder Free -4.6grams
DESIGN	: Ambidextrous. Beaded Cuff
SURFACE	: Palm Textured/Finger Textured /Smooth
COLOUR	:White & Blue
PROTEIN LEVEL	: N/A
POWDER CONTENT	: Max 2.0 mg/glove
FORCE AT BREAK	: Before Ageing :6.0-9.0N After Ageing: 6.0-9.0N
TENSILE STRENGTH	: Before Ageing: 14-18 Mpa After Ageing: 14-18 Mpa
ELONGATION	: Before Ageing: 500-600 % After Ageing: 400-500 %
PERFORMANCE STANDARD	: ASTM D-3578, EN 455-Part 1,2&3
MATERIAL	:100% pure Nitrile
DONNING AID	: Chlorinated/Polymer
STORAGE CONDITION	: Product shall be stored under room condition, avoid direct sunlight
SHELF LIFE	: Product shall have shelf life of 3 years from date of manufacture with the above storage condition.
SIZE	:XS-X small,S-Small, M-Medium, L-Large,XL-X Large
DIMENSION	: Length: Min 240mm
CRITERIA	: Average Width (mm): XS-78±3,S-85±3, M-95±3, L-105±3, XL-115±3,
WEIGHT	: Average Weight (grams): XS-3.8±0.3, S-4.2±0.3,M-4.6±0.3, L-5.0± 0.3, XL-5.4 ± 0.3
THICKNESS	: Single Wall thickness (x 0.01mm) Finger thickness:11±3mm Palm thickness:10±2mm



JR^U MEDICAL^E 乔润医疗

